

# CRYSTIC<sup>®</sup> 781PALV

## Polyester Resin for Resin Transfer Moulding

### Introduction

Crystic 781PALV is a pre-accelerated, orthophthalic polyester resin, designed for use in RTM and RTM Light processes. A non-accelerated version of this resin is available, as Crystic 781LV.

### Applications

Crystic 781PALV is especially suited to those Resin Transfer Moulding applications which require the addition of filler to the resin system. In RTM Light applications Crystic 781PALV is recommended to be used un-filled.

### Features and Benefits

The viscosity characteristics of Crystic 781PALV allow the addition of up to 40 parts per hundred of filler, with no adverse effect on flow properties. This means that the filled resin mix can be easily injected into the RTM mould. In RTM Light applications the viscosity characteristics of Crystic 781PALV ensure excellent flow through the mould. Crystic 781PALV has good mechanical properties and impact resistance.

### Formulation

Crystic 781PALV should be allowed to attain workshop temperature (18°C — 20°C) before use. It requires only the addition of a catalyst to start the curing reaction. The recommended catalyst is Trigonox 44B (acetyl acetone peroxide), which should be added at 1-2% into the resin. Trigonox 524, an acetyl acetone peroxide/tert-butyl peroxybenzoate mixture developed specifically to obtain a more efficient cure in RTM, can also be used. Geltimes of Crystic 781PALV can be approximately determined from the Table below.

### Pot Life

Temperature	Pot Life in minutes using Trigonox 44B		
	1.0	1.5	2.0
Pot life in minutes at 20°C	-	-	8.5
Pot life in minutes at 25°C	-	-	6
Pot life in minutes at 40°C	5	3.5	2

The resin, mould and workshop should be at, or above 15°C before curing is carried out.

### Additives

The addition of pigment pastes, fillers or other additives can adversely affect the Resin Transfer Moulding process and the properties of the cured laminate. Users should consult Scott Bader's Technical Service Department before making any such additions.

### Post Curing

For optimum properties, laminates made using Crystic 781PALV should be post cured before being put into service. The laminate should be allowed to cure for 24 hours at 20°C, and then be oven cured for a minimum of 16 hours at 40°C or 3 hours at 80°C.

### Typical Properties

The following tables give typical properties of Crystic 781PALV when tested in accordance with the appropriate BS or BS EN ISO test method.

Property		Liquid Resin
Appearance		Mauvish
Viscosity at 25 °C	Poise	1.75
Volatile Content	%	42
Specific Gravity at 25 °C		1.09
Stability at 20 °C	months	3
Geltime at 20 °C using 2% Trigonox 44B	minutes	8.5
Property		Fully Cured* Resin (unfilled casting)
Barcol Hardness (Model GYZJ 934-1)		48
Deflection Temperature under load † (1.80 MPa)	°C	78
Water Absorption 24 hours at 23°C	mg	19
Tensile Strength	MPa	72
Tensile Modulus	MPa	3600
Elongation at Break	%	3.1
Specific Gravity at 20°C		1.2

\* Curing schedule – 24 hours at 20 °C, 3 hours at 80°C

† Curing schedule – 24 hours at 20 °C, 5 hours at 80°C, 3 hours at 120°C

Property		C.S.M** Laminate
Glass Content	%	28
Tensile Strength	MPa	96
Tensile Modulus	MPa	7400
Elongation at Break	%	1.6
Flexural Strength	MPa	184
Flexural Modulus	MPa	5800
Notched Izod Impact Strength	kJ/m <sup>2</sup>	74
Charpy Impact Strength	kJ/m <sup>2</sup>	70

\*\* Made with 1 layer Rovicore 600 D3 600  
Curing schedule – 24 hours at 20°C, 16 hours at 40°C

**Storage**

Crystic 781PALV should be stored in the dark in suitable closed containers. It is recommended that the storage temperature should be less than 20°C where practical, but should not exceed 30°C. Ideally, containers should be opened only immediately prior to use.

**Packaging**

Crystic 781PALV is supplied in 25kg, 200kg and 1 tonne containers. Bulk supplies can be delivered by road tanker.

**Health & Safety**

Please see separate Material Safety Data Sheet.

Version 2 : February 2013

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

**SCOTT BADER COMPANY LIMITED**

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

[www.scottbader.com](http://www.scottbader.com)